



BALLISTIC AND FORCED ENTRY RATING: MEETS OR EXCEEDS THE FOLLOWING

- UL752 LEVEL I BALLISTIC STANDARD
- · NIJ 0108.1 LEVEL IIA
- EN 1062 LEVEL BR2
- ASTM F356I TO THREAT LEVEL 8
- ASTM FI233

TECHNICAL DATA

THIS BALLISTIC GLAZING WILL WITHSTAND 3 ROUNDS OF 9MM IN A ONE SQUARE FOOT SAMPLE, UTILIZING A FMJ PROJECTILE WITH A MASS OF 124 GRAIN (8 GRAM) TRAVELING AT 1293 FEET / SECOND (394.I METERS / SECOND) WITH EACH ROUND DELIVERING AN IMPACT OF 625 JOULES OF ENERGY AND A MOMENTUM OF 3.17 KG M/S. THIS BALLISTIC GLAZING MAY ALSO PROVIDE UP TO 20 MINUTES OF FORCED ENTRY PROTECTION.

- NOMINAL THICKNESS: 9/16"; 0.544"; 13.817MM
- WEIGHT PER SQUARE FOOT: 5.15LB; 2.33KG

GLAZING OPTIONS

- CLEAR
- LOW IRON

CONTACT US FOR ADDITIONAL GLASS TYPES & GLAZING OPTIONS

FRAMING OPTIONS

- ALUMINUM STORE FRONT
- ALUMINUM CURTAIN WALL

SIZING INFORMATION

· UP TO 70" X I30"

TESTING CERTIFICATIONS

- NTS 21219-001
- · NTS BGAI9004-I



TESTED TO

3 ROUNDS

OF 9MM



