SCHOOL SAFE PREMIUM™

ATTACK SIDE



VARIOUS INTERLAYERS

GLASS, POLYCARBONATE &

POLYURETHANE

TESTED TO 3 ROUNDS 0F 9MM



SPECIFICATIONS

WEIGHT

5.15LB

BALLISTIC AND FORCED ENTRY RATING: MEETS OR EXCEEDS THE FOLLOWING

 TESTED TO UL752 LEVEL 1 BALLISTIC PENETRATION STANDARD (THIS IS A LOW-SPALL PRODUCT, NOT A NO-SPALL PRODUCT)

0.544"

- ASTM F3561 TO THREAT LEVEL 8
- ASTM F1233

TECHNICAL DATA

THIS BALLISTIC GLAZING WILL WITHSTAND 3 ROUNDS OF 9MM IN A ONE SQUARE FOOT SAMPLE, UTILIZING A FMJ PROJECTILE WITH A MASS OF 124 GRAIN (8 GRAM) TRAVELING AT 1293 FEET / SECOND (394.1 METERS / SECOND) WITH EACH ROUND DELIVERING AN IMPACT OF 625 JOULES OF ENERGY AND A MOMENTUM OF 3.17 KG M/S. THIS BALLISTIC GLAZING MAY ALSO PROVIDE UP TO 20 MINUTES OF FORCED ENTRY PROTECTION.

- NOMINAL THICKNESS: 9/16"; 0.544"; 13.817MM
- WEIGHT PER SQUARE FOOT: 5.15LB; 2.33KG



LEVEL 1 LOW SPALL GLAZING

GLAZING OPTIONS

- CLEAR
- LOW IRON

CONTACT US FOR ADDITIONAL GLASS TYPES & GLAZING OPTIONS

FRAMING OPTIONS

- ALUMINUM STORE FRONT
- ALUMINUM CURTAIN WALL

SIZING INFORMATION

• UP TO 70" X 126"

TESTING CERTIFICATIONS

- NTS 21219-001
- NTS BGA19004-1

BALLISTICGLASSANDARMOR.COM



